



---

# ARDEX R 65 P

## Water-Based Polyurethane Sealer

---

To protect & seal floor, stone and tile surfaces

Penetrates & cures within the pores of the surface  
providing a seal for extended service life

Low odour

Minimal visual appearance

Good water & chemical resistance

Good abrasion resistance

UV Resistant

Dust suppression

---



本企业通过ISO9001:2000质量认证体系



ARDEX (HONGKONG) CO., LTD  
Unit D, 16/F, CNT Tower, No.388  
Hennessy Road,  
Wan Chai, Hong Kong  
TEL: 852-25296325  
FAX: 852-25298615

ARDEX (SHANGHAI) CO., LTD  
3F, Building 13, No. 505,  
South Zhongshan Rd.,  
Shanghai, China  
TEL: 86-21 61526722  
FAX: 86-21 61526726  
P.C.: 200010

# ARDEX R 65 P

## Water-Based Polyurethane Sealer

### DESCRIPTION

ARDEX R65P is a two-component water-based polyurethane sealer designed for protecting surfaces such as concrete, stone, tile, terrazzo, pavers, ARDEX K320 floors, etc from wear & staining.

### FEATURES/BENEFITS

- interior / exterior use
- tough
- UV resistant
- water & chemical resistant
- water-based
- can be re-coated

### SUBSTRATE PREPARATION

It is essential that ARDEX R65 P is applied to sound, clean and dry surfaces to ensure maximum adhesion.

### MIXING

The entire contents of the component B container should be poured into the component A container and the two materials mixed thoroughly for at least 3 minutes using a heavy duty slow speed drill and spiral paddle. Note: Once mixed, the ARDEX R65 P will lose working time if it is left in the mixing container or otherwise kept in bulk.

### COATING

Once mixed the ARDEX R65 P should be poured in to a paint tray and applied without delay onto the prepared surface using a short pile roller. Ensure that the entire surface is coated and that the substrate is fully wet out. 'Ponding' of the material is to be avoided.

Apply in thin coats. At least 2 coats are recommended for best performance.

When using new rollers, ensure that all loose fibres are removed prior to use, any loose fibres released from the roller will cause unsightly blemishes in the finished coating..

### LIMITATIONS

These products should not be applied at temperatures less than 12°C or where the ambient relative humidity is greater than 85%.

Once the mixed material has exceeded its pot life the viscosity and the characteristics of the product changes and any unused product should be discarded at this time.

**Note:** The rate of wear of this coating will be increased in areas of concentrated foot traffic and vehicle traffic, in particular doorways, work benches, drinks dispensers, etc.

### TOOL CLEANING

ARDEX R65 P can be removed from tools and equipment by washing in clean water immediately after use. Any hardened coating will need to be removed mechanically.

### PROPERTIES

The values shown are typical of results obtained in the laboratory at 23°C & 50%RH. Actual performance values obtained on site may vary from those quoted.

### PHYSICAL PROPERTIES

ARDEX R65 P @ 23°C / 50%RH

Colour	Part A:	white
	Part B:	clear
	Dry:	clear
	Finish:	satin – matt, varies depending on number of coats

Pot life:	30 minutes
Recoat Time:	3 – 24 hours
Foot traffic:	24 hours
Full cure:	7 days.

This time will vary depending upon the condition of the surface and the ambient temperature. Provision for ventilation and air movement will be required.

VOC: 77 g/L [GB/T 22374-2008]

### MAINTENANCE

Good housekeeping and regular cleaning is essential in order to maintain the performance of ARDEX R65P. It is particularly important in areas that are subject to regular spillage. Spillages should not be allowed to dry as this results in higher concentrations of the materials, which may lead to early failure.

### COVERAGE ESTIMATES

Approx. 25-35m<sup>2</sup> per 6.6kg pack

Note: These coverage figures are theoretical, actual coverage rates will be determined by the nature of substrates and wastage.

### PACKAGING

ARDEX R65P is a two component system consisting of Parts A (resin – 6kg) and Parts B (hardener – 0.6kg) packed in plastic buckets.

### STORAGE AND SHELF LIFE

ARDEX R65P has a shelf life of not less than 6 months if kept in a dry store between 5°C and 35°C in the original unopened containers. The product should be protected from frost, kept away from direct sunlight and sources of heat.

### PRECAUTIONS

ARDEX R 65 P should not come into contact with the skin and eyes or be swallowed. Ensure adequate ventilation and avoid inhalation of vapours. Wear suitable gloves, goggles and other protective clothing. The use of barrier creams can provide additional skin protection. When working in confined areas suitable respiratory equipment must be used. In case of contact with skin, rinse with plenty of clean water then wash with soap and water. Do not use solvent. In case of contact with eyes, rinse immediately with plenty of clean water, then seek medical attention without delay. If swallowed, seek medical attention straight away, do not induce vomiting.

### DISPOSAL/SPILLAGE

Spillage of any of the component products should be absorbed onto sand or other inert material and transferred to a suitable disposable vessel. Disposal of such spillage or empty packaging should be in accordance with local waste disposal authority regulations.

For further information please refer to the Material Safety Data Sheet (MSDS)

The technical details, recommendations and other information contained in this datasheet are given in good faith and represents the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable National or Local Standard, our instructions & recommendations, and only for the uses they are intended. Regional specific recommendations, standards, codes of practice, building regulations or industry guidelines may affect specific installation recommendations. Our Company policy is one of continuous Research & Development; we therefore reserve the right to update this information at any time without prior notice. We guarantee the consistent high quality of our products; however, as we have no control over site conditions or the execution of the work, we accept no liability for any loss or damage which may arise as a result thereof. The supply of our products and services is also subject to certain terms, warranties & exclusions; and these details will be made available to you on request. You should make yourself familiar with them.